

Q8 T 55 85W-140

API GL-5 axle fluid

Description

Q8 T 55 85W-140 is an advanced heavy duty gear lubricant. The specifically selected base oils and additives offer optimum lubrication in extreme pressure and shock loading situations. They are recommended for heavy duty axles requiring API GL-5 specification.

Applications

Q8 T 55 85W-140 is recommended for heavy duty components such as rear axles, final drives or differentials, especially those having hypoid gears. It meets the API GL-5 specification and is applicable for on- and off-highway, construction, light and heavy duty trucks and commercial vehicles, operating under high speed/shock load, high speed/low torque or low speed/high torque conditions.

Benefits

- Exceptional wear protection under heavy duty operating conditions.
- Outstanding protection against wear and extends component life.
- Superb gear protection under shock load conditions.
- Outstanding protection against rust and corrosion.
- Very shear stable formulation

Specifications, recommendations and approvals

API	GL-5	MIL	L-2105D
Case	MS 1316	Rockwell International	O-76
Clark	ALC-1 5M 7-80 KE	Volvo	97310
Clark	MS-8 Rev. 1	ZF	
Clark	TLC-25 3M 8-83	ZF	TE-ML 05A
Ford	SM-2C-1011A	ZF	TE-ML 07A
Ford	SQM-2C9002-AA	ZF	TE-ML 12A
John Deere	JDM J11E	ZF	TE-ML 16B
Komatsu Dresser	B22-0003	ZF	TE-ML 16C
Komatsu Dresser	B22-0005	ZF	TE-ML 16D
MAN	342 Type M1	ZF	TE-ML 17B
MB	235.0	ZF	TE-ML 19B
MIL	L-2105B	ZF	TE-ML 21A

Color code blue = officially approved

Properties

	Method	Unit	Typical
Density, 20 °C	D 4052	g/ml	0,909
Density, 15 °C	D 4052	g/ml	0,912
Viscosity Grade	-	-	SAE 85W-140
Kinematic Viscosity, 40 °C	D 445	mm²/s	386,6
Kinematic Viscosity, 100 °C	D 445	mm²/s	28,1
Viscosity Index	D 2270	-	100
Brookfield Viscosity, -12 °C	D 2983	Pa.s	69
Pour Point	D 97	°C	-15
Flash Point, COC	D 92	°C	220
Brookfield Viscosity, -12 °C	D 2983	Pa.s	69

The figures above are not a specification. They are typical figures obtained within production tolerances.

Remarks

Product Data Sheet includes a selection of specifications, for full overview please consult the Q8Oils website.

