Industrial gear oil



# Q8 Goya 680

Classic performance industrial gear oil

## Description

*Q8* Goya 680 is an advanced mineral oil that meets the current standards for gear lubricants and provides high industrial performance. Its oxidation and thermal stability guarantee a long service life of the lubricant. Q8 Goya 680 provides an optimum wear and corrosion protection under all conditions and has a minimal downtime thanks to a high load carrying capacity.

# **Applications**

Q8 Goya 680 is used in mid to high loaded industrial gearboxes, paper and steel mills, cement and mining, plastic extrusion and injection, aerators and agitators. It is also applied in non-gear applications including shaft couplings, screws and mid to high loaded plains and rolling contact bearings (slow speed).

#### Benefits

- Minimizes downtime which leads to a higher maintenance efficiency
- Advanced anti-wear characteristics
- Advanced protection against corrosion
- Highly resistant to oil deterioration

## Specifications & Approvals

| ANSI/AGMA | 9005-F16    | Danieli | Standard 0.000.001-R15 (2020) |
|-----------|-------------|---------|-------------------------------|
| DIN       | 51517-3 CLP | ISO     | 12925-1 CKC-CKD               |

#### **Properties**

|  | Method    | Unit       | Typical |
|--|-----------|------------|---------|
| ISO Viscosity Grade                    | -         | -          | 680     |
| Density, 15 °C                         | D 4052    | g/ml       | 0,906   |
| Kinematic Viscosity, 40 °C             | D 445     | mm²/s      | 680     |
| Kinematic Viscosity, 100 °C            | D 445     | mm²/s      | 39.3    |
| Viscosity Index                        | D 2270    | -          | 96      |
| Total Acid Number                      | D 974     | mg KOH/g   | 0.5     |
| Pour Point                             | D 97      | °C         | -9      |
| Flash Point, COC                       | D 92      | °C         | 250     |
| Carbon Residue                         | D 524     | % mass     | 1.35    |
| Foam, 5 min blowing, seq. 1-2-3        | D 892     | ml         | 0/0/0   |
| Foam, 10 min settling, seq. 1-2-3      | D 892     | ml         | 0/0/0   |
| Rust Test, Proc. A and B, 24 h         | D 665     | -          | pass    |
| Copper Strip, 3 h, 100 °C              | D 130     | -          | 1a      |
| Four Ball Test, Weld Load              | IP 239    | Ν          | 4000    |
| Four Ball Wear, 196 N, 54 °C, 1800 rpm | D 4172    | mm         | 0.33    |
| Timken, OK Load                        | D 2782    | Ν          | 311     |
| Mean Hertz Load                        | -         | Ν          | 592     |
| FZG Test, A/8.3/90                     | DIN 51354 | load stage | >12     |

The figures above are not a specification. They are typical figures obtained within production tolerances.

## Remarks

Miscible and compatible with mineral and PAO-based gear oils.