

## Q8 Goya 680

Classic performance industrial gear oil

### Description

Q8 Goya 680 is an advanced mineral oil that meets the current standards for gear lubricants and provides high industrial performance. Its oxidation and thermal stability guarantee a long service life of the lubricant. Q8 Goya 680 provides an optimum wear and corrosion protection under all conditions and has a minimal downtime thanks to a high load carrying capacity.

### Applications

Q8 Goya 680 is used in mid to high loaded industrial gearboxes, paper and steel mills, cement and mining, plastic extrusion and injection, aerators and agitators. It is also applied in non-gear applications including shaft couplings, screws and mid to high loaded plains and rolling contact bearings (slow speed).

### Benefits

- Minimizes downtime which leads to a higher maintenance efficiency
- Advanced anti-wear characteristics
- Advanced protection against corrosion
- Highly resistant to oil deterioration

### Specifications & Approvals

<b>ANSI/AGMA</b>	9005-E02 8 EP	<b>Danieli</b>	Standard 0.000.001-R15 (2023)
<b>ANSI/AGMA</b>	9005-F16	<b>ISO</b>	12925-1 CKC-CKD
<b>DIN</b>	51517-3 CLP		

### Properties

	Method	Unit	Typical
ISO Viscosity Grade	-	-	680
Colour	D 1500	-	4,5
Density, 15 °C	D 4052	g/ml	0,919
Density, 20 °C	D 4052	g/ml	0,915
Kinematic Viscosity, 40 °C	D 445	mm <sup>2</sup> /s	680
Kinematic Viscosity, 100 °C	D 445	mm <sup>2</sup> /s	41,2
Viscosity Index	D 2270	-	100
Pour Point	D 97	°C	-9
Flash Point, COC	D 92	°C	248
Foam, 5 min blowing, seq. 1-2-3	D 892	ml	10/20/10
Foam, 10 min settling, seq. 1-2-3	D 892	ml	0/0/0
Rust Test, Proc. A and B, 24 h	D 665	-	pass
Copper Strip, 3 h, 100 °C	D 130	-	1
Four Ball Test, Weld Load	IP 239	N	4000
Timken, OK Load	D 2782	N	311
FZG Test, A/8.3/90	DIN 51354	load stage	>12

The figures above are not a specification. They are typical figures obtained within production tolerances.

### Remarks

Miscible and compatible with mineral and PAO-based gear oils.

## Sustainability

*The product Carbon Footprint (PCF), cradle-to-gate (Q8Oils state of the art facility in Belgium), of Q8 Goya 680 is **1.33** kg CO<sub>2</sub>eq / kg.*

*Please contact Q8Oils to learn more about the positive environmental impact, the handprint, of this product.*

*To ensure accuracy and reliability, the PCF calculation tool has been verified by an independent third party. The verification report is available in the disclaimer.*

*For more info check [here](#)*



**we  
take  
care**