

Q8 Handel 15

Zinc-based hydraulic oil with very high viscosity index

Description

Q8 Handel 15 is an excellent zinc-based hydraulic oil that is suitable for a wide range of temperatures and applications. Thanks to its very high viscosity index of >210, the zinc-based oil has exceptional flow properties. The high oxidation stability assures an extended drain interval and lubricant life. Q8 Handel 15 is used in demanding applications that require very high viscosity index oils.

Applications

Q8 Handel 15 is used in all season applications, off-highway equipment. It is also applied in industries and applications requiring high viscosity index oils, such as in paper, steel, cement, mining industry.

Benefits

- Lower downtime and an improved maintenance efficiency
- Extends service life time thus minimal costs and maximal efficiency
- Zinc included technology
- Exceptionally high viscosity index
- Optimum air release
- Outstandingly resistant to oil deterioration
- Exceptionally suitable for use in all seasons
- Optimum separation of water

Specifications & Approvals

Bosch Rexroth
DIN

RE 90220 notes
51524-3 HVLP

Eaton Brochure
ISO

03-401-2010
11158 HV

Properties

	Method	Unit	Typical
ISO Viscosity Grade	-	-	15
Density, 15 °C	D 4052	g/ml	0,869
Colour	D 1500	-	L 0.5
Kinematic Viscosity, 40 °C	D 445	mm ² /s	15.53
Kinematic Viscosity, 100 °C	D 445	mm ² /s	4.39
Viscosity Index	D 2270	-	215
Pour Point	D 97	°C	-60
Total Acid Number	D 974	mg KOH/g	0.52
Total Acid Number	D 664	mg KOH/g	0.1 after 1000h
Flash Point, COC	D 92	°C	152
Emulsion, Distilled Water, 54.4 °C	D 1401	-	40-40-0 (20 min)
Foam, 5 min blowing, seq. 1-2-3	D 892	ml	60/30/60
Foam, 10 min settling, seq. 1-2-3	D 892	ml	0/0/0
Rust Test, Proc. A and B, 24 h	D 665	-	pass
Copper Strip, 3 h, 100 °C	D 130	-	1a

The figures above are not a specification. They are typical figures obtained within production tolerances.

Sustainability

The product Carbon Footprint (PCF), cradle-to-gate (Q8Oils state of the art facility in Belgium), of Q8 Handel 15 is **1.56** kg CO₂eq / kg.

Please contact Q8Oils to learn more about the positive environmental impact, the handprint, of this product.

To ensure accuracy and reliability, the PCF calculation tool has been verified by an independent third party. The verification report is available in the disclaimer.

For more info check [here](#)



**we
take
care**