

Q8 Unishift PC Synt 75W

Synthetic API GL-4 manual transmission fluid

Description

Q8 Unishift PC Synt 75W is a superior manual transmission fluid for passenger cars and light duty vehicles. This versatile lubricant offers exceptional protection and durability, even under extreme pressure, and provides best-in-class thermal stability, making it suitable for a wide variety of passenger car applications. It meets the requirements of most OEMs based on API GL-4.

Applications

Q8 Unishift PC Synt 75W is a versatile lubricant designed to be used in passenger cars and light duty synchromesh manual gearboxes and transaxles, specifically in high load carrying situations. It meets the API GL-4 specification and the requirements of most European and Asian manufacturers.

Benefits

- Exceptional low temperature fluidity and wide temperature operating range.
- Exceptional internal friction reduction.
- Excellent easy gear shifting at low temperatures.
- Superior protection against wear and extends component life.
- Superior protection against rust and corrosion.

Specifications, recommendations and approvals

GL-4	PSA	9730-A8
JWS 2271	PSA	B71 2310
MTF-LT2	VAG	VW G 052 171
MTF-LT3	VAG	VW G 052 512
9.55550-MZ14	VAG	VW G 052 527
9.55550-MZ2	VAG	VW G 052 527
9.55550-MZ27	VAG	VW G 052 549
9.55550-MZ6	VAG	VW G 052 798
M2C200-D1	VAG	VW G 52 726
M2C200-D2	VAG	VW TL 521 71 (G 052 171 A1/A2)
MTF 0063	VAG	VW TL 521 78 (G 052 178 A2)
235.71	VAG	VW TL 525 12 (G 052 512 A2)
	JWS 2271 MTF-LT2 MTF-LT3 9.55550-MZ14 9.55550-MZ2 9.55550-MZ27 9.55550-MZ6 M2C200-D1 M2C200-D2 MTF 0063	JWS 2271 PSA MTF-LT2 VAG MTF-LT3 VAG 9.55550-MZ14 VAG 9.55550-MZ2 VAG 9.55550-MZ27 VAG 9.55550-MZ6 VAG M2C200-D1 VAG M2C200-D2 VAG MTF 0063 VAG

Properties

	Method	Unit	Typical	
Density, 15 °C	D 4052	g/ml	0,847	
Viscosity Grade	-	-	SAE 75W	
Kinematic Viscosity, 40 °C	D 445	mm²/s	33	
Kinematic Viscosity, 100 °C	D 445	mm²/s	6.8	
Viscosity Index	D 2270	-	172	
Brookfield Viscosity, -40 °C	D 2983	Pa.s	44	
Pour Point	D 97	°C	-39	
Flash Point P-M	D 93	°C	195	

The figures above are not a specification. They are typical figures obtained within production tolerances.

Sustainability

The product Carbon Footprint (PCF), cradle-to-gate (Q80ils state of the art facility in Belgium), of Q8 Unishift PC Synt 75W is $1.38~\rm kg~CO_2eq/kg$.

Please contact Q80ils to learn more about the positive environmental impact, the

handprint, of this product.
To ensure accuracy and reliability, the PCF calculation tool has been verified by an independent third party. The verification report is available in the disclaimer.
For more info check here



