

Q8 Haydn 68

Advanced zinc-based hydraulic oil

Description

Q8 Haydn 68 oil consists of a zinc-based additive technology. This oil can be used in all sorts of operational applications and industrial equipment. Q8 Haydn 68 oil has an optimum thermal and oxidation stability and has a long service life time.

Applications

Q8 Haydn 68 is suitable for all kinds of systems, general industrial hydraulic applications and other industrial applications (low charged gears, pumps, compressors, bearings).

Benefits

- Lower downtime and an improved maintenance efficiency
- Zinc-based additives
- Advanced performance against wear
- Excellent separation of water
- Advanced release of entrained air bubbles

Specifications & Approvals

Bosch Rexroth	RE 90220 notes	ISO	11158 HM
DIN	51517-2 CL	MAG IAS	P-68, P-69, P-70
DIN	51524-2 HLP	Parker Hannifin	HF-0, HF-1, HF-2
Danieli	Standard 0.000.001-R15 (2023)	Swedish Standard	SS 155434 AM
Eaton Brochure	03-401-2010		

Properties

	Method	Unit	Typical
ISO Viscosity Grade	-	-	68
Colour	D 1500	-	2
Density, 15 °C	D 4052	g/ml	0,88
Density, 20 °C	D 4052	g/ml	0,875
Kinematic Viscosity, 40 °C	D 445	mm ² /s	68
Kinematic Viscosity, 100 °C	D 445	mm ² /s	8.9
Viscosity Index	D 2270	-	105
Pour Point	D 97	°C	-30
Flash Point, COC	D 92	°C	225
Emulsion, Distilled Water, 54.4 °C	D 1401	-	40-40-0(20)
Foam, 5 min blowing, seq. 1-2-3	D 892	ml	10/20/10
Foam, 10 min settling, seq. 1-2-3	D 892	ml	0/0/0
Rust Test, Proc. A and B, 24 h	D 665	-	pass
Copper Strip, 3 h, 100 °C	D 130	-	1
FZG Test, A/8.3/90	DIN 51354	load stage	12

The figures above are not a specification. They are typical figures obtained within production tolerances.

Sustainability

The product Carbon Footprint (PCF), cradle-to-gate (Q8Oils state of the art facility in Belgium), of Q8 Haydn 68 is **1.24** kg CO₂eq / kg.

Please contact Q8Oils to learn more about the positive environmental impact, the handprint, of this product.

To ensure accuracy and reliability, the PCF calculation tool has been verified by an independent third party. The verification report is available in the disclaimer.

For more info check [here](#)



**we
take
care**

PRODUCT CARBON FOOTPRINT
METHOD VALIDATED BY:

PCF CALCULATION IN LINE WITH:
ISO 14067 | ATIEL-UEIL PCF

