PRODUCT DATA SHEET

Q8 Trans XGS 75W-85

Full synthetic total driveline SAE J2360 transmission fluid

Description

Q8 Trans XGS 75W-85 is a superior transmission fluid designed for heavy duty driveline components requiring special low temperature fluidity. The product offers best-in-class protection against extreme pressure and wear due to exceptional stability in high as well as low temperatures. This results in optimized lubrication of hypoid and non-hypoid axles.

Applications

Q8 Trans XGS 75W-85 is designed for heavy duty drive-line components such as rear-axles, final drives and selected manual transmissions, requiring special low temperature fluidity to reduce fuel consumption or facilitate gear shifting.

Benefits

- *Exceptional low temperature fluidity and wide temperature operating range.*
- *Exceptional internal friction reduction.*
- *Superior axle wear protection.*
- *Exceptional wear protection under heavy duty operating conditions.*
- *Superior protection against rust and corrosion.*

Specifications, recommendations and approvals

API	GL-4	**Iveco**	18-1807 MG
API	GL-5	**Iveco**	18-1807 MGM
Fiat	9.55550-DA3	**MB**	235.10
Fiat	9.55550-DA4	**MB**	235.63
Fiat	9.55550-DA8	**Meritor**	GO MTR 076S
Fiat	9.55550-MX3	**Nissan**	MTF HQ
Fiat	9.55550-MX4	**SAE**	J 2360
Fiat	9.55550-MZ1	**VAG**	VW G 052 190
Fiat	9.55550-MZ3		

Properties

	Method	Unit	Typical
Density, 15 °C	*D 4052*	*g/ml*	*0,869*
Viscosity Grade	*-*	*-*	*SAE 75W-85*
Kinematic Viscosity, 40 °C	*D 445*	*mm²/s*	*77.5*
Kinematic Viscosity, 100 °C	*D 445*	*mm²/s*	*12.7*
Viscosity Index	*D 2270*	*-*	*164*
Brookfield Viscosity, -40 °C	*D 2983*	*Pa.s*	*50*
Pour Point	*D 97*	*°C*	*<-42*
Flash Point, COC	*D 92*	*°C*	*175*

The figures above are not a specification. They are typical figures obtained within production tolerances.

Remarks

The original equipment manufacturer's recommendation should always be followed.

Sustainability

*The product Carbon Footprint (PCF), cradle-to-gate (Q8Oils state of the art facility in Belgium), of Q8 Trans XGS 75W-85 is **1.27** kg CO_2eq / kg.*
Please contact Q8Oils to learn more about the positive environmental impact, the handprint, of this product.
To ensure accuracy and reliability, the PCF calculation tool has been verified by an independent third party. The verification report is available in the disclaimer.
For more info check here

we take care

PRODUCT CARBON FOOTPRINT
METHOD VALIDATED BY:

PCF CALCULATION IN LINE WITH:
ISO 14067 | ATIEL-UEIL PCF

VINÇOTTE